

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification <sup>5</sup> :  C08F 4/649, 10/00</p>	<p>A1</p>	<p>(11) International Publication Number: WO 93/02110  (43) International Publication Date: 4 February 1993 (04.02.93)</p>
<p>(21) International Application Number: PCT/US92/05366 (22) International Filing Date: 24 June 1992 (24.06.92)  (30) Priority data: 730,363 15 July 1991 (15.07.91) US  (71) Applicants: EXXON CHEMICAL PATENTS INC. [US/ US]; 1900 East Linden Avenue, Linden, NJ 07036 (US). UNIVERSITY OF MASSACHUSETTS LOWELL [US/ US]; 450 Aiken Street, Lowell, MA 01854 (US).  (72) Inventors: FAUST, Rudolf ; 580 Concord Avenue, Lexing- ton, MA 02173 (US). GYOR, Miklos ; Osaka University, International House, Toyonaka-shi, 1-1, Machikaneya- ma-cho, Osaka 560 (US). WANG, Hsien-Chang ; 14 Whittier Street, Edison, NJ 08837 (US).</p>		<p>(74) Agent: SCHNEIDER, John, E.; Exxon Chemical Com- pany, P.O. Box 710, 1900 East Linden Avenue, Linden, NJ 07036 (US).  (81) Designated States: AU, CA, JP, KR, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IT, LU, MC, NL, SE).  Published With international search report.</p>
<p>(54) Title: LIVING CARBOCATIONIC POLYMERIZATION PROCESS</p> <p>(57) Abstract</p> <p>An olefin polymerization process is provided wherein an olefin chargestock is contacted with an organic compound polym- erization initiator, a Lewis acid coinitiator and a pyridine compound such as 2,6-di-tert-butylpyridine to produce homopolymers, copolymers or block copolymers having a narrow molecular weight distribution.</p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FI	Finland	MI	Mali
AU	Australia	FR	France	MN	Mongolia
BB	Barbados	GA	Gabon	MR	Mauritania
BE	Belgium	GB	United Kingdom	MW	Malawi
BF	Burkina Faso	GN	Guinea	NL	Netherlands
BG	Bulgaria	GR	Greece	NO	Norway
BJ	Benin	HU	Hungary	PL	Poland
BR	Brazil	IE	Ireland	RO	Romania
CA	Canada	IT	Italy	RU	Russian Federation
CF	Central African Republic	JP	Japan	SD	Sudan
CG	Congo	KP	Democratic People's Republic of Korea	SE	Sweden
CH	Switzerland	KR	Republic of Korea	SN	Senegal
CI	Côte d'Ivoire	LJ	Liechtenstein	SU	Soviet Union
CM	Cameroon	LK	Sri Lanka	TD	Chad
CS	Czechoslovakia	LU	Luxembourg	TC	Togo
DE	Germany	MC	Monaco	US	United States of America
DK	Denmark	MG	Madagascar		
ES	Spain				

- 1 -

## LIVING CARBOCATIONIC POLYMERIZATION PROCESS

### BACKGROUND OF THE INVENTION

#### 1. Field of the Invention

The present invention relates to a process for the polymerization of olefins. The process is a living polymerization process. The term "living polymerization" is used herein to describe a polymerization process which is theoretically terminationless and which is not susceptible to chain transfer.

#### 2. Description of Information Disclosures

Living polymerization processes are known.

U.S. Patent 4,910,321 discloses a living carbocationic polymerization process utilizing initiation systems containing an organic acid or ester and a Lewis acid which may be  $\text{TiCl}_4$ , although the preferred Lewis acid is  $\text{BCl}_3$ , to produce homopolymers, random copolymers, block copolymers and the like.

U. S. Patent 4,908,421 discloses a living cationic polymerization process for producing a terminally functional polymer utilizing a catalyst system containing a Lewis acid and an organic peroxy compound wherein the monomer charge comprises isobutylene and the organic peroxy compound in an amount ranging from  $10^{-4}$  to  $10^{-1}$  moles per mole of the isobutylene. The Lewis acid may be  $\text{TiCl}_4$ . See also European patent application 8930737377.5 filed July 29, 1989, now Publication No. 0355997 published February 28, 1990.

It has also been proposed to obtain narrow molecular weight distribution polyisobutylenes by utilizing a  $\text{BCl}_3$ /ester initiator and a 2,6-di-tert-butyl pyridine proton trap.

It has now been found that an olefin polymerization process conducted in the presence of a specified initiator system yields polymers having

- 2 -

improved properties as will become apparent in the ensuing description.

#### SUMMARY OF THE INVENTION

In accordance with the invention, there is provided a process for polymerizing an olefin which comprises the step of contacting an olefin chargestock with

- (A) an organic compound selected from the group consisting of an alcohol, an ester, an ether, an organic halide and mixtures thereof;
- (B) a Lewis acid;
- (C) a pyridine compound selected from the group consisting of 2,6-di-tert-butylpyridine, a substituted 2,6-di-tert-butylpyridine, and mixtures thereof,

at polymerization conditions in a polymerization zone, to produce a polymer.

#### BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 is a graph showing the number average molecular weight ( $\bar{M}_n$ ) versus weight in grams of polyisobutylene formed [WPB(g)] in the polymerization of isobutylene in the presence of a specified initiator system.

Figure 2 is a graph showing the number average molecular weight versus monomer conversion (%) in the polymerization of isobutylene and a specified initiator system.

Figure 3 is a graph showing the number average molecular weight versus monomer conversion (%) in the polymerization of isobutylene using specified initiator systems.

Figure 4 is a graph showing the number average molecular weight versus monomer conversion (%) in the polymerization of isobutylene and a specified initiator system.

- 3 -

Figure 5 is a graph showing number average molecular weight versus weight of polyisobutylene formed (g) in the polymerization of isobutylene and a specified initiator system.

Figure 6 is a graph showing number average molecular weight versus monomer conversion (%) in the polymerization of styrene and specified initiator systems.

#### DETAILED DESCRIPTION OF THE INVENTION

The process of the present invention comprises contacting a chargestock containing a single type of olefins or more than one type of olefins in a polymerization zone at polymerization conditions with a initiator system comprising polymerization initiator, herein referred to a Component A, a coinitiator, herein referred to as Component B, and a proton trap, herein referred to as Component C to produce olefin derived polymers having a narrow molecular weight distribution (MWD). The polymerization is a living polymerization process.

##### The Initiator System

The initiator system comprises Component A, Component B, and Component C.

##### Component A - The Initiator


Component A is an organic compound polymerization initiator selected from the group consisting of an alcohol, an ester, an ether, an organic halide and mixtures thereof. Suitable alcohols include alcohols represented by the formula:



wherein R is an alkyl group, a substituted alkyl group, an aryl group, a substituted aryl group, having from 2 to 20, preferably 9 to 15 carbon atoms, and n ranges from 1 to 20, preferably from 1 to 4.

- 4 -


Suitable esters include esters represented by the formula:



wherein R and R' are independently selected from the group consisting of an alkyl group, a substituted alkyl group, an aryl group, a substituted aryl group, having from 2 to 20, preferably 9 to 15 carbon atoms, and n ranges from 1 to 20, preferably from 1 to 4.

Suitable ethers include ethers represented by the formula  $\text{R}-(\text{-O-R}')_n$ , wherein R and R' are independently selected from the group consisting of an alkyl group, a substituted alkyl group, an aryl group, a substituted aryl group, having from 2 to 20 preferably 9 to 15 carbon atoms, and n ranges from 1 to 20, preferably from 1 to 4.

Suitable organic halides include organic halides represented by the formula



wherein R, R', and R'' are each independently selected from the group consisting of an alkyl group, and a substituted alkyl group, an aryl group, a substituted aryl group, having from 2 to 20, preferably 9 to 15 carbon atoms and n ranges from 1 to 20, preferably from 1 to 4, and wherein X is a halogen selected from the group consisting of chlorine, bromine and mixtures thereof. The alkyl group, in the above given formulas may be a saturated alkyl group or an unsaturated alkyl group, e.g. an allyl group.

- 5 -

Component B - The Co-Initiator

Component B is a Lewis acid co-initiator. Suitable Lewis acids include  $\text{BCl}_3$ ,  $\text{BF}_3$ ,  $\text{AlCl}_3$ ,  $\text{SnCl}_4$ ,  $\text{TiCl}_4$ ,  $\text{SbF}_5$ ,  $\text{SeCl}_3$ ,  $\text{ZnCl}_2$ ,  $\text{FeCl}_3$ ,  $\text{VCl}_4$ ,  $\text{AlR}_n\text{Cl}_{3-n}$ , wherein R is an alkyl group and n is less than 3, and mixtures thereof. The preferred Lewis acid for use in the present invention is  $\text{TiCl}_4$ . Desirably, the amount of Lewis acid relative to the amount of Component A (initiator) is selected to be at least equal to a stoichiometric amount. Preferably, the number of moles of Lewis acid ranges from about 2 to about 40 times the stoichiometric amount relative to Component A.

Component C

Component C, a proton trap, is a pyridine compound selected from the group consisting of 2,6-di-tert-butylpyridine (DTBP), substituted 2,6-di-tert-butylpyridine and mixtures thereof.

Suitable substituted 2,6-di-tert-butylpyridines include 2,6-di-tertiarybutylalkylpyridines such as, for example, 2,6-di-tert-butyl-4-methylpyridine.

When protic impurities (e.g., moisture, acids) are present in the polymerization zone, the pyridine compound is preferably present in at least a stoichiometric amount relative to the protic impurities. More preferably, the pyridine compound is present in an amount greater than the stoichiometric amount relative to the protic impurities.

The Olefinic Chargestock

The olefinic (monomer) chargestock comprises at least a single type of olefin or it may comprise more than one type of olefins depending on the desired final polymer. Suitable olefins include a  $\text{C}_4$  to  $\text{C}_7$  isomonoolefin, a  $\text{C}_4$  to  $\text{C}_{14}$  multiolefin, a vinylidene aromatic compound which may be substituted or unsubstituted, and mixtures thereof. The preferred  $\text{C}_4$

- 6 -

to C<sub>17</sub> isomonoolefin is isobutylene. The preferred C<sub>4</sub> to C<sub>14</sub> multiolefin is isoprene.

The preferred vinylidene aromatic compound is selected from the group consisting of styrene, alkylstyrene and mixtures thereof. The preferred alkylstyrenes are a para-methyl-styrene, and an alpha-methylstyrene.

When the olefinic chargestock comprises a C<sub>4</sub> to C<sub>7</sub> isomonoolefin such as isobutylene and a C<sub>4</sub> to C<sub>14</sub> multiolefin such as a conjugated diolefin, the molar ratio of isomonoolefin to multiolefin may range from about 1000:1 to about 10:1, preferably from about 200:1 to about 40:1.

Block polymers may also be produced by the polymerization of the present invention, for example, by the sequential addition of an isomonoolefin and a second monomer such as a conjugated diolefin (see, for example, U.S. Patent 4,910,261, the teachings of which are hereby incorporated by reference) or a vinylidene aromatic compound.

The process of the present invention may be conducted in the presence or in the absence of a diluent. Suitable diluents include C<sub>1</sub> to C<sub>4</sub> halogenated hydrocarbons, such as methyl chloride and methylene dichloride, C<sub>5</sub> to C<sub>8</sub> aliphatic hydrocarbons, such as pentane, hexane, and heptane and C<sub>5</sub> to C<sub>10</sub> cyclic hydrocarbons, such as cyclohexane and methyl cyclohexane, and mixtures thereof.

The order of addition of Component A, Component B, and Component C to the olefinic chargestock is not critical. For example, Component A and Component B may be premixed, optionally in a diluent, and added to the olefinic chargestock which may also comprise an optional diluent.

A preferred order of addition is as follows: diluent (if present), olefin chargestock, Component A (initiator), Component C (proton trap), Component B (co-initiator).



- 7 -

The polymerization process is conducted in a polymerization zone of a conventional polymerization apparatus, in the presence or in the absence of a diluent. Suitable polymerization conditions include a temperature ranging from about minus 100°C to about plus 10°C, preferably from about minus 80°C to about 0°C for a time period ranging from about 1 to about 180 minutes (hours). Preferably, the polymerization reaction mixture may be subjected to agitation using conventional mixing means.

The polymers produced by the process of the present invention may be homopolymers, copolymers, terpolymers, etc., block copolymers and the like depending upon the olefinic chargestock used.

The number average molecular weight ( $\bar{M}_n$ ) of the polymers of the present invention may range from about 500 to about 2,000,000, preferably from about 20,000 to about 300,000. The polymers have a narrow molecular weight distribution such that the ratio of weight average molecular weight to number average molecular weight ( $\bar{M}_w/\bar{M}_n$ ) of the polymers ranges from about 1.0 to about 1.5, preferably from about 1.0 to about 1.2. The polymers may be recovered from the polymerization zone effluent and finished by conventional methods.

The following examples are presented to illustrate the invention.

#### EXAMPLE 1

A series of polymerization experiments were carried out in large test tubes immersed into a heptane bath (-80°C) under nitrogen atmosphere in a MBraun M-150 glove box. Total volume of the reaction mixture was 25 ml. Addition sequence of the reactants was as follows: diluent mixture - monomer - initiator - proton trap - coininitiator. AMI (All Monomer In), and IMA (Incremental Monomer Addition) experiments were carried out. Using the AMI technique, parallel runs

- 8 -

were quenched at different reaction times. From the yield of the polymers and gel permeation chromatography (GPC) data, the percent conversion-time dependencies,  $\bar{M}_w/\bar{M}_n$ , and initiator efficiency were obtained. Simultaneously, control runs were carried out in which only the coinitiator and proton trap were charged in the absence of an initiator. Negligible amount of polymer (3%) was obtained in the control runs.

In Example 1, polymerization of IB (isobutylene) was initiated with 5-tert.-butyl-1,3-dicumyl-methylether in the presence of DTBP by the IMA technique. The results are summarized in Figure 1 which shows polymerization of IB initiated with 5-tert.-butyl-1,3-dicumyl-methylether in the presence of DTBP. IMA technique; Time between monomer additions: 30 mins;  $[t\text{-Bu-DiCuOMe}] = 9.25 \times 10^{-4} \text{ M}$ ;  $[\text{TiCl}_4] = 1.48 \times 10^{-2} \text{ M}$ ;  $V_0 = 25 \text{ mL}$ . Diluent:  $\text{CH}_3\text{Cl}:\text{n-Hexane}$ , 40:60 v:v; Temperature:  $-80^\circ\text{C}$ . In Figure 1 number average molecular weight ( $\bar{M}_n$ ) is plotted against WPIB (g), that is, weight in grams of polyisobutylene formed and the numbers on the plot are molecular weight distribution (MWD) values.

The IMA method means incremental monomer addition. The AMI method, All Monomer In, means that all the monomer is added before the start of the polymerization, as described in R. Faust, and J. P. Kennedy, J. Polymer Science, Polymer Chem. A25, 1847 (1987).

#### EXAMPLE 2

Polymerization experiments were also carried out using the AMI technique under the same experimental conditions as in Example 1 utilizing IB chargestock in the presence of DTBP and as initiator 5-tert.-butyl-1,3-dicumyl-methyl ether, as follows: in the presence and in the absence of DTBP, Initiator: 5-tert.-butyl-1,3-dicumyl-methylether using AMI technique.  $[\text{IB}]_0 = 2.04 \text{ M}$   $[t\text{-Bu-DiCuOMe}] = 1 \times 10^{-3} \text{ M}$ ;  $[\text{TiCl}_4] = 1.6 \times 10^{-2} \text{ M}$ ;

- 9 -

$V_0 = 25$  mL. Diluent:  $\text{CH}_3\text{Cl}:\text{n-Hexane}$ , 40:60 (v:v); Temperature:  $-80^\circ\text{C}$ . The results are summarized in Figure 2 in which number average molecular weight ( $\bar{M}_n$ ) is plotted against conversion (%) of the monomer to the polymer.

#### EXAMPLE 3

In this experiment methylcyclohexane was used instead of n-hexane in the polymerization of isobutylene with the t-BudicUOME/ $\text{TiCl}_4$ / $\text{CH}_3\text{Cl}:\text{methylcyclohexane}$  (40:60 v/v), at  $-80^\circ\text{C}$  system in the absence and presence of a proton trap (DTBP)  $[\text{t-BudicUOME}] = 9.24 \times 10^{-4}$  M;  $[\text{TiCl}_4] = 1.48 \times 10^{-2}$  M. The results are summarized in Figure 3.

#### EXAMPLE 4

In this example 5-tert.-butyl-1,3-dicumyl-chloride was used as initiator in the polymerization of isobutylene as follows:

Polymerization of IB with 5-tert.-butyl-1,3-dicumyl-chloride as initiator in the presence of proton trap DTBP. AMI technique,  $[\text{IB}]_0 = 2.04$  M  $[\text{t-Bu-DiCuCl}] = 1 \times 10^{-3}$  M;  $[\text{TiCl}_4] = 1.6 \times 10^{-2}$  M;  $V_0 = 25$  mL. Solvent:  $\text{CH}_3\text{Cl}:\text{n-Hexane}$ , 40:60 (v:v); Temperature:  $-80^\circ\text{C}$ . The results are summarized in Figure 4.

#### EXAMPLE 5

In this example IMA technique was followed with 5-tert.-butyl-1,3-dicumyl-chloride as initiator. The experiment was conducted as follows:

Polymerization of IB initiated with 5-tert.-butyl-1,3-dicumyl-chloride. IMA technique (4 x 1 ml); Time elapsed between monomer additions: 30 mins;  $[\text{t-Bu-DiCuCl}] = 1 \times 10^{-3}$  M;  $[\text{TiCl}_4] = 1.6 \times 10^{-2}$  M;  $V_0 = 25$  mL;  $[\text{DTBP}] = 1 \times 10^{-3}$  M; Diluent:  $\text{CH}_3\text{Cl}:\text{n-Hexane}$ , 40:60 (v:v); Temperature:  $-80^\circ\text{C}$ . The numbers are MWD values. The results are summarized in Example 5.

- 10 -

EXAMPLE 6

In this example styrene was used as monomer as follows:

t-BudicUOMe/TiCl<sub>4</sub>/CH<sub>3</sub>Cl:MeCH, 40:60 (v:v) system at minus 80°C in the absence and presence of proton trap (DTBP). The results are summarized in Figure 6.

As can be seen from Examples 1 to 6, when the polymerization experiments were carried out in the presence of proton trap (DTBP), deviations from the theoretical line decrease with increasing DTBP concentration and at [DTBP] =  $1-2 \times 10^{-3}$  mole/l, close to theoretical molecular weights and narrow MWDs were observed. Independent measurements indicated that this concentration was equal to the concentration of protic impurities in the system.

Preparation of Triblock Copolymers

Based on Examples 1 to 6, related to the living polymerization of isobutylene and styrene, polymerization conditions were obtained under which living polymerization of isobutylene and styrene can be carried out by sequential monomer addition to obtain block copolymers. Block copolymerizations by sequential monomer addition were carried out in a 250 ml three neck flasks equipped with overhead stirrer.

Polymerization parameters:

[Initiator] =  $1 \times 10^{-3}$  M

[TiCl<sub>4</sub>, Coinitiator] =  $1.6 \times 10^{-2}$  M

[DTBP] =  $2 \times 10^{-3}$  M

Diluent: MeCl/methylcyclohexane (40/60 v/v)

Temperature: -80°C

Isobutylene added: 12 ml (= 8.4 g)

Styrene added: 3.9 ml

Styrene polymerization time: 5 minutes

- 11 -

The method of monomer addition strongly affects the outcome of styrene polymerization: Using pure (undiluted) styrene leads to temporary freezing of this monomer at the moment of addition into the  $-80^{\circ}\text{C}$  solution. Freezing can be eliminated by diluting the monomer. Using methylcyclohexane in volume ratio 1:4 (3.5 ml styrene + 14 ml MeCH) the polar/apolar volume ratio of the reaction medium changed from 40:60 in favor of the apolar components (MeCH and St) at the beginning of St (styrene) polymerization. The properties of triblocks obtained can be compared from the stress-strain data.

EXAMPLE 7

In this example, 5-t-butyl-1,3-bis(1-methoxy-1-methylethyl) benzene initiator was used; undiluted styrene was added, and the DTBP concentration was  $1 \times 10^{-3}$  M.

<u>Sample No.</u>	<u>PSt</u>	<u>PIB</u>	<u>PSt</u>	<u>M<sub>w</sub>/M<sub>n</sub></u>
A	15500	85000	15500	1.43

PSt means polystyrene

PIB means polyisobutylene

$\overline{M}_w/\overline{M}_n$  is the ratio of weight average molecular weight to number average molecular weight.

EXAMPLE 8

In this example, 5-t-butyl-1,3 bis (1-acetoxy-1-methylethyl) benzene initiator was used; styrene was added undiluted.

<u>Sample No.</u>	<u>PSt</u>	<u>PIB</u>	<u>PSt</u>	<u>M<sub>w</sub>/M<sub>n</sub></u>
B	14300	78000	14300	1.53

- 12 -

EXAMPLE 9

In this example, 5-t-butyl-1,3 bis (1-chloro-1-methylethyl) benzene initiator was used; styrene was diluted with methyl cyclohexane (1/4; v/v) and the DTBP concentration was  $1 \times 10^{-3}$  M.

<u>Sample No.</u>	<u>PSt</u>	<u>PIB</u>	<u>PSt</u>	<u>Mw/Mn</u>
C	8066	70900	8066	1.13

EXAMPLE 10

In this example, same initiator was used as initiator used in Example 9; styrene was diluted with methyl cyclohexane (1/4; v/v).

<u>Sample No.</u>	<u>PSt</u>	<u>PIB</u>	<u>PSt</u>	<u>Mw/Mn</u>
D	7082	82500	7082	1.11

EXAMPLE 11

In this example, same initiator as in Example 9 was used; styrene was diluted with methyl cyclohexane (1/4; v/v) and the DTBP concentration was  $4 \times 10^{-3}$  M.

<u>Sample No.</u>	<u>PSt</u>	<u>PIB</u>	<u>PSt</u>	<u>Mw/Mn</u>
E	7154	78200	7154	1.21

EXAMPLE 12

In this example, same initiator as in Example 9 was used; styrene was diluted with methyl cyclohexane (1/4; v/v), and the styrene reaction time was 10 minutes.

<u>Sample No.</u>	<u>PSt</u>	<u>PIB</u>	<u>PSt</u>	<u>Mw/Mn</u>
F	14400	84000	14400	1.19

EXAMPLE 13

In this example, same initiator as in Example 9 was used; styrene was diluted with methyl cyclohexane

- 13 -

(1/4; v/v), the polymerization temperature was minus 90°C, and the styrene reaction time was 10 minutes.

<u>Sample No.</u>	<u>PSt</u>	<u>PIB</u>	<u>PSt</u>	<u>M<sub>w</sub>/M<sub>n</sub></u>
G	6380	80300	6380	1.19

EXAMPLE 14

In this example, same initiator as in Example 9 was used; styrene was diluted with methyl cyclohexane (1/4; v/v), and the styrene reaction time was 15 minutes.

<u>Sample No.</u>	<u>PSt</u>	<u>PIB</u>	<u>PSt</u>	<u>M<sub>w</sub>/M<sub>n</sub></u>
H	13900	89300	13900	1.13

EXAMPLE 15

In this example, same initiator as in Example 9 was used; styrene was diluted with methyl cyclohexane (1/4; v/v), the polymerization temperature was minus 90°C, and the styrene reaction time was 15 minutes.

<u>Sample No.</u>	<u>PSt</u>	<u>PIB</u>	<u>PSt</u>	<u>M<sub>w</sub>/M<sub>n</sub></u>
I	14600	86900	14600	1.12

The Stress-Strain data are summarized in Table I.

- 14 -

TABLE I  
Stress-Strain Data

<u>Sample No.</u>	<u>100% Mod.</u>	<u>300% Mod.</u>	<u>500% Mod.</u>	<u>Tensile Strength psi</u>	<u>Elongation %</u>
A	110	347	1084	1830	625
B	112	322	931	2195	615
C	45	55	84	490	1000
D	63	114	237	1898	865
E	40	75	135	725	850
F	85	221	947	2700	650
G	44	35	52	75	850
H	88	200	890	3000	690
I	85	197	967	3600	750

The test methods used are shown in Table II.

TABLE II

<u>Property</u>	<u>Test Method</u>
100% Modulus, psi	ASTM D412
300% Modulus, psi	ASTM D412
500% Modulus, psi	ASTM D412
Tensile Strength, psi	ASTM D412
Elongation, %	ASTM D412

EXAMPLE 16

In this example, 1-chloro, 2,4,4-trimethyl pentane was used as initiator.  $[M] = 2.0 \text{ M}$ ,  $[I] = 5.1 \times 10^{-2} \text{ M}$ ,  $[\text{TiCl}_4] = 1.2 \times 10^{-1} \text{ M}$ ,  $[\text{DTBP}] = 2 \times 10^{-3} \text{ M}$ , temperature =  $-40^\circ\text{C}$ , solvent: n-hexane- $\text{CH}_3\text{Cl}$  60/40 v/v. The PIB prepared this way had  $M_n = 2200$ ,  $MWD = 1.14$ .



- 15 -

EXAMPLE 17

In this example, 2-chloro, 2-phenyl propane was used as initiator.  $[M] = 3.7 \text{ M}$ ,  $[I] = 9.44 \times 10^{-2} \text{ M}$ ,  $[\text{TiCl}_4] = 1.9 \times 10^{-1} = [\text{DTBP}] = 2 \times 10^{-3} \text{ M}$ , temperature =  $-60^\circ\text{C}$ , solvent: n-hexane- $\text{CH}_3\text{Cl}$ , 60/40 v/v.

a) The PIB obtained by the AMI technique exhibited  $M_n = 2300$ ,  $MWD = 1.3$ .

b) The PIB prepared by continuously feeding isobutylene, equivalent to the amount in example 16, to the solution containing the initiator, coinitiator and DTBP exhibited  $MWD = 1.08$ .

- 16 -

## CLAIMS:

1. A process for polymerizing an olefin which comprises the step of contacting an olefin chargestock with

(A) an organic compound selected from the group consisting of an alcohol, an ester, an ether, an organic halide and mixtures thereof;

(B) a Lewis acid comprising  $\text{TiCl}_4$ ; and

(C) a pyridine compound selected from the group consisting of 2,6-di-tert-butylpyridine, a substituted 2,6-di-tert-butylpyridine, and mixtures thereof;

at polymerization conditions in a polymerization zone, to produce a polymer.

2. The process of claim 1, wherein protic impurities are present in said polymerization zone and wherein said pyridine compound present in said zone is at least a stoichiometric amount relative to said protic impurities.

3. The process of claim 2, wherein said said pyridine compound present in said zone is greater than the said stoichiometric amount relative to said protic impurities.

4. The process of claim 1, wherein said substituted 2,6-di-tert-butyl pyridine is 2,6-di-tert-butyl-4-methyl-pyridine.

5. The process of claim 1 wherein said Lewis acid is  $\text{TiCl}_4$ .

- 17 -

6. The process of claim 5, wherein the number of moles of said  $\text{TiCl}_4$  in said polymerization zone is present in at least a stoichiometric amount relative to said (A) organic compound.

7. The process of claim 5, wherein said number of moles of said  $\text{TiCl}_4$  ranges from about 2 to 40 times stoichiometric amount relative to said (A) organic compound.

8. The process of claim 1, wherein said olefin chargestock comprises an olefin selected from the group consisting of  $\text{C}_4$  to  $\text{C}_7$  isomonoolefin,  $\text{C}_4$  to  $\text{C}_{14}$  multiolefins a vinylidene aromatic compound and mixtures thereof.

9. The process of claim 8, wherein said vinylidene aromatic compound is styrene.

10. The process of claim 8, wherein said vinylidene aromatic compound is an alkylstyrene selected from the group consisting of alpha-methylstyrene, para-methylstyrene and mixtures thereof.

11. The process of claim 1, wherein said organic compound is an organic halide.

12. The process of claim 1, wherein said polymerization conditions include a temperature ranging from about minus  $100^\circ\text{C}$  to about plus  $10^\circ\text{C}$ .

13. The process of claim 1, wherein said polymerization zone additionally comprises a diluent.

14. The process of claim 13, wherein said diluent is selected from the group consisting of  $\text{C}_1$  to  $\text{C}_4$  halogenated hydrocarbons,  $\text{C}_5$  to  $\text{C}_8$  aliphatic

- 18 -

hydrocarbons, C<sub>5</sub> to C<sub>10</sub> cyclic hydrocarbons, and mixtures thereof.

15. The process of claim 1, wherein said polymer has a number average molecular weight ranging from about 500 to about 2,000,000.

16. The process of claim 1, wherein said polymer has a number average molecular weight ranging from about 20,000 to about 300,000.

17. The process of claim 1, wherein said polymer has a narrow molecular weight distribution.

1 / 6




FIG. 1

2 / 6




FIG. 2

SUBSTITUTE SHEET

3 / 6




FIG. 3

SUBSTITUTE SHEET

4 / 6




FIG. 4



5 / 6




FIG. 5

6 / 6




FIG. 6

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 92/05366

<b>I. CLASSIFICATION OF SUBJECT MATTER</b> (If several classification symbols apply, indicate all) <sup>6</sup> According to International Patent Classification (IPC) or to both National Classification and IPC IPC <sup>5</sup> : C 08 F 4/649, C 08 F 10/00														
<b>II. FIELDS SEARCHED</b> <div style="text-align: center; border-top: 1px solid black; border-bottom: 1px solid black; margin: 5px 0;">Minimum Documentation Searched <sup>7</sup></div> <table style="width: 100%; border-collapse: collapse;"> <tr> <th style="width: 20%; text-align: left; border-bottom: 1px solid black;">Classification System</th> <th style="text-align: left; border-bottom: 1px solid black;">Classification Symbols</th> </tr> <tr> <td style="border-right: 1px solid black; padding: 5px;">IPC<sup>5</sup></td> <td style="padding: 5px;">C 08 F 4/00, C 08 F 10/00, C 08 F 12/00, C 08 F 297/00</td> </tr> </table> <div style="text-align: center; border-top: 1px solid black; border-bottom: 1px solid black; margin: 5px 0;">Documentation Searched other than Minimum Documentation to the extent that such Documents are included in the Fields Searched <sup>8</sup></div>			Classification System	Classification Symbols	IPC <sup>5</sup>	C 08 F 4/00, C 08 F 10/00, C 08 F 12/00, C 08 F 297/00								
Classification System	Classification Symbols													
IPC <sup>5</sup>	C 08 F 4/00, C 08 F 10/00, C 08 F 12/00, C 08 F 297/00													
<b>III. DOCUMENTS CONSIDERED TO BE RELEVANT</b> <sup>9</sup> <table style="width: 100%; border-collapse: collapse;"> <tr> <th style="width: 10%; text-align: left; border-bottom: 1px solid black;">Category <sup>10</sup></th> <th style="text-align: left; border-bottom: 1px solid black;">Citation of Document, <sup>11</sup> with indication, where appropriate, of the relevant passages <sup>12</sup></th> <th style="width: 15%; text-align: left; border-bottom: 1px solid black;">Relevant to Claim No. <sup>13</sup></th> </tr> <tr> <td style="border-right: 1px solid black; text-align: center; vertical-align: top; padding: 5px;">X</td> <td style="border-right: 1px solid black; padding: 5px;">US, A, 4 946 899 (KENNEDY et al.) 07 August 1990 (07.08.90), see claims 1-3, 5-12; examples.</td> <td style="text-align: center; vertical-align: top; padding: 5px;">1-17</td> </tr> <tr> <td style="border-right: 1px solid black; text-align: center; vertical-align: top; padding: 5px;">X</td> <td style="border-right: 1px solid black; padding: 5px;">Journal of Macromolecular Science-Chemistry, vol. A18, no. 1, issued 1982 (Dekker Journals, New York), J.P. KENNEDY et al. "Carbo- cationic Polymerization in the Presence of Sterically Hindered Bases", see pages 1-152.</td> <td style="text-align: center; vertical-align: top; padding: 5px;">1-17</td> </tr> <tr> <td style="border-right: 1px solid black; text-align: center; vertical-align: top; padding: 5px;">A</td> <td style="border-right: 1px solid black; padding: 5px;">EP, A2, 0 397 081 (NIPPON ZEON CO., LTD.) 14 November 1990 (14.11.90), see claims 1, 4, 5; examples.</td> <td style="text-align: center; vertical-align: top; padding: 5px;">1-3, 5- 17</td> </tr> </table>			Category <sup>10</sup>	Citation of Document, <sup>11</sup> with indication, where appropriate, of the relevant passages <sup>12</sup>	Relevant to Claim No. <sup>13</sup>	X	US, A, 4 946 899 (KENNEDY et al.) 07 August 1990 (07.08.90), see claims 1-3, 5-12; examples.	1-17	X	Journal of Macromolecular Science-Chemistry, vol. A18, no. 1, issued 1982 (Dekker Journals, New York), J.P. KENNEDY et al. "Carbo- cationic Polymerization in the Presence of Sterically Hindered Bases", see pages 1-152.	1-17	A	EP, A2, 0 397 081 (NIPPON ZEON CO., LTD.) 14 November 1990 (14.11.90), see claims 1, 4, 5; examples.	1-3, 5- 17
Category <sup>10</sup>	Citation of Document, <sup>11</sup> with indication, where appropriate, of the relevant passages <sup>12</sup>	Relevant to Claim No. <sup>13</sup>												
X	US, A, 4 946 899 (KENNEDY et al.) 07 August 1990 (07.08.90), see claims 1-3, 5-12; examples.	1-17												
X	Journal of Macromolecular Science-Chemistry, vol. A18, no. 1, issued 1982 (Dekker Journals, New York), J.P. KENNEDY et al. "Carbo- cationic Polymerization in the Presence of Sterically Hindered Bases", see pages 1-152.	1-17												
A	EP, A2, 0 397 081 (NIPPON ZEON CO., LTD.) 14 November 1990 (14.11.90), see claims 1, 4, 5; examples.	1-3, 5- 17												
<div style="display: flex; justify-content: space-between;"> <div style="width: 45%;"> <p><sup>14</sup> Special categories of cited documents: <sup>15</sup></p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubt on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> </div> <div style="width: 45%;"> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</p> <p>"Z" document member of the same patent family</p> </div> </div>														
<b>IV. CERTIFICATION</b> <table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; border-bottom: 1px solid black; padding: 5px;">           Date of the Actual Completion of the International Search  <div style="text-align: center;">01 October 1992</div> </td> <td style="width: 50%; border-bottom: 1px solid black; padding: 5px;">           Date of Mailing of this International Search Report  <div style="text-align: center;">19. 10. 92</div> </td> </tr> <tr> <td style="border-bottom: 1px solid black; padding: 5px;">           International Searching Authority  <div style="text-align: center;">EUROPEAN PATENT OFFICE</div> </td> <td style="border-bottom: 1px solid black; padding: 5px;">           Signature of Authorized Officer  <div style="text-align: center;">PUSTERER e.h.</div> </td> </tr> </table>			Date of the Actual Completion of the International Search <div style="text-align: center;">01 October 1992</div>	Date of Mailing of this International Search Report <div style="text-align: center;">19. 10. 92</div>	International Searching Authority <div style="text-align: center;">EUROPEAN PATENT OFFICE</div>	Signature of Authorized Officer <div style="text-align: center;">PUSTERER e.h.</div>								
Date of the Actual Completion of the International Search <div style="text-align: center;">01 October 1992</div>	Date of Mailing of this International Search Report <div style="text-align: center;">19. 10. 92</div>													
International Searching Authority <div style="text-align: center;">EUROPEAN PATENT OFFICE</div>	Signature of Authorized Officer <div style="text-align: center;">PUSTERER e.h.</div>													

**ANHANG**

zum internationalen Recherchen-  
bericht über die internationale  
Patentanmeldung Nr.

**ANNEX**

to the International Search  
Report to the International Patent  
Application No.

**ANNEXE**

au rapport de recherche inter-  
national relatif à la demande de brevet  
international n°

PCT/US 92/05366 SAE 61847

In diesem Anhang sind die Mitglieder  
der Patentfamilien der im obenge-  
nannten internationalen Recherchenbericht  
angeführten Patentdokumente angegeben.  
Diese Angaben dienen nur zur Unter-  
richtung und erfolgen ohne Gewähr.

This Annex lists the patent family  
members relating to the patent documents  
cited in the above-mentioned inter-  
national search report. The Office is  
in no way liable for these particulars  
which are given merely for the purpose  
of information.

La présente annexe indique les  
membres de la famille de brevets  
relatifs aux documents de brevets cités  
dans le rapport de recherche inter-  
national visée ci-dessus. Les renseigne-  
ments fournis sont donnés à titre indica-  
tif et n'engagent pas la responsabilité  
de l'Office.

Im Recherchenbericht angeführtes Patentdokument Patent document cited in search report Document de brevet cité dans le rapport de recherche		Datum der Veröffentlichung Publication date Date de publication	Mitglied(er) der Patentfamilie Patent family member(s) Membre(s) de la famille de brevets	Datum der Veröffentlichung Publication date Date de publication
US A	4946899	07-08-90	keine - none - rien	
EP A2	397081	14-11-90	JP A2 3174403 EP A3 397081	29-07-91 12-02-92